

Silirub 908

Revision: 15/04/2019

Page 1 from 2

Technical data

Basis	Polysiloxane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 8 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	40 ± 5 Shore A
Density**	Ca. 1.40 g/ml
Elastic recovery (ISO 7389)**	> 80 %
Maximum allowed distortion	25 %
Max. tension (ISO 37)**	Ca. 1,00 N/mm ²
Elasticity modulus 100% (ISO 37)**	0,60 N/mm ²
Elongation at break (ISO 37)**	Ca. 400 %
Temperature resistance**	-50 °C → 150 °C
Application temperature	5 °C → 40 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Silirub 908 is a high-quality, neutral, elastic one-component silicone based joint sealant.

Properties

- Very easy to apply
- Colourfast and UV resistant
- Permanently elastic after curing
- Very good adhesion on many materials
- Neutral curing

Applications

- All usual building joints with high movement.
- Glazing and joint works.
- Expansion joints between many different construction materials.
- Sealing between PVC, treated wooden and metal profiles and glass.

Packaging

Colour: white, black, other colors on request
Packaging: 280ml koker

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Substrates

Substrates: all usual building substrates

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces should be primed with Primer 150. Prepare non-porous surfaces with a Soudal activator or cleaner (see Technical Data Sheet).

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion test on any substrate. In contact with certain surfaces such as bitumen or copper, discoloration may occur due to reaction with the substrate. On PVC we recommend a preliminary adhesion test. Certain paints and textured coatings on aluminum profiles can influence the adhesion.

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth. Three-point adhesion should be avoided at all time. Too small joint dimensions can have the effect that the silicone is pulled off because of too large movements.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Silirub 908

Revision: 15/04/2019

Page 2 from 2

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

Remarks

- Direct contact with the secondary sealing of insulating glass units (insulation) and the PVB-film of safety glass must be avoided.
- Because of the diversity we recommend to do adhesion tests on aluminum lackers, textured coating and PVC before application.
- In an acid environment or in a dark room, a white sealant can slightly turn yellow. Under the influence of sunlight it will turn back to its initial colour.
- When finished with a finishing solution or soapy solution, make sure that the surfaces are not touched by this solution. This will cause the sealant not to adhere to that surface. Therefore we recommend to only dip the finishing tool in this solution.
- Do not use in applications where continuous water immersion is possible.
- Do not use on polycarbonate. Use Silirub PC instead.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Silirub 908 cannot be used on natural stone.
- Not suitable for bonding aquariums.

- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.
- When applying, make sure not to spill any sealant on the surface of materials. Taping the surface around the joint can prevent this.

Environmental clauses*Lead regulation:*

Silirub 908 conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.